



AMERICAN BILTRITE

AB-263

60 DURO NEOPRENE (55% CR BASE) / PREMIUM GRADE / PLATE FINISH / BLACK / VERY GOOD OIL RESISTANCE / TRIMMED / WITH POWDER

GAUGE	ITEM NUMBER 36"	ITEM NUMBER 48"	ITEM NUMBER 60"
SPECIFICATION: 3BC609A14C12E034			
1/32"	264-02-362 (S)	264-02-482 (S)	N/A
1/16"	264-04-362 (S)	264-04-482 (S)	264-04-602 (S)
3/32"	264-06-362 (S)	264-06-482 (S)	N/A
1/8"	264-08-362 (S)	264-08-482 (S)	264-08-602 (S)
3/16"	264-12-362	264-12-482 (S)	264-12-602 (S)
1/4"	264-16-362 (S)	264-16-482 (S)	264-16-602 (S)
3/8"	264-24-362	264-24-482 (S)	N/A
1/2"	264-32-362	264-32-482 (S)	N/A
5/8"	264-40-362	264-40-482	N/A
3/4"	264-48-362	264-48-482	N/A
1"	264-64-362	264-64-482	N/A

(S) Normally available from inventory.

STANDARD DIMENSIONS

GAUGE	TOLERANCE (+/-)	ROLL LENGTH		APPROX. WEIGHT PER ROLL		APPROX. SQ. FT. PER ROLL	
		36"	48"	36"	48"	36"	48"
1/32"	.012	300'	250'	207 LBS.	230 LBS.	900 SQ. FT.	1000 SQ. FT.
1/16"	.016	150'	125'	198 LBS.	220 LBS.	450 SQ. FT.	500 SQ. FT.
3/32"	.016	75'	65'	149 LBS.	172 LBS.	225 SQ. FT.	260 SQ. FT.
1/8"	.020	75'	65'	198 LBS.	229 LBS.	225 SQ. FT.	260 SQ. FT.
3/16"	.031	60'	45'	238 LBS.	238 LBS.	180 SQ. FT.	180 SQ. FT.
1/4"	.031	45'	35'	238 LBS.	246 LBS.	135 SQ. FT.	140 SQ. FT.
3/8"	.047	45'	35'	357 LBS.	370 LBS.	135 SQ. FT.	140 SQ. FT.
1/2"	.047	45'	35'	475 LBS.	493 LBS.	135 SQ. FT.	140 SQ. FT.
5/8"	.063	30'	30'	396 LBS.	528 LBS.	90 SQ. FT.	120 SQ. FT.
3/4"	.093	30'	30'	475 LBS.	634 LBS.	90 SQ. FT.	120 SQ. FT.
1"	.100	30'	25'	634 LBS.	704 LBS.	90 SQ. FT.	100 SQ. FT.

Maximum pieces per roll: 1/32" to 1/2" - 2 pieces, 5/8" to 1" - 1 piece

Minimum piece length: 10'

Length tolerance: 1/16" to 1/2" +/-10%,
5/8" to 1" +10%, Min. 10'

GAUGE	ROLL LENGTH 60"	WEIGHT / ROLL 60"	SQ. FT. / ROLL 60"
1/16"	100'	220 LBS.	500 SQ. FT.
1/8"	65'	286 LBS.	325 SQ. FT.
3/16"	65'	429 LBS.	325 SQ. FT.
1/4"	35'	308 LBS.	175 SQ. FT.

Minimum Order:

Inventory Item: 1 Roll

Non-inventory Item: 2,000 lbs.

Custom Made Item: 3,000 lbs.

AB-263 PHYSICAL PROPERTIES

DESCRIPTION	TYPICAL VALUE	UNITS
POLYMER	CR/SBR	
HARDNESS	60	SHORE "A" DUROMETER
TENSILE	1000	PSI
ELONGATION	300	%
OIL AGING # 3 OIL	70 HOURS	100 ° C
CHANGED-HARDNESS	-30	POINTS
CHANGED-TENSILE	-42	%
CHANGED-ELONGATION	-41	%
CHANGED-MASS	34	%
CHANGED-VOLUME	53	%