



# AMERICAN BILTRITE

# AB-265

60 DURO NEOPRENE BLEND / INDUSTRIAL GRADE / PLATE FINISH / BLACK / MODERATE OIL RESISTANCE / TRIMMED / WITH PLASTIC LINER (NO POWDER)

GAUGE	ITEM NUMBER 36"	ITEM NUMBER 48"
<b>SPECIFICATION: BC610</b>		
1/32"	296-02-362 (S) *P	265-02-482 (S)
1/16"	265-04-362 (S)	265-04-482 (S)
3/32"	265-06-362 (S)	265-06-482 (S)
1/8"	265-08-362 (S)	265-08-482 (S)
3/16"	265-12-362 (S)	265-12-482 (S)
1/4"	265-16-362 (S)	265-16-482 (S)
3/8"	265-24-362 (S)	265-24-482 (S)
1/2"	265-32-362 (S)	265-32-482 (S)
5/8"	265-40-362 (S)	265-40-482 (S)
3/4"	265-48-362 (S)	265-48-482 (S)
1"	265-64-362 (S)	265-64-482 (S)

(S) Normally available from inventory.

Note: All other items available with powder - minimum quantities apply.

\*P - Powdered -- No Plastic Liner

## STANDARD DIMENSIONS

GAUGE	TOLERANCE (+/-)	ROLL LENGTH		APPROX. WEIGHT PER ROLL		APPROX. SQ. FT. PER ROLL	
		36"	48"	36"	48"	36"	48"
1/32"	.012	300'	250'	207 LBS.	230 LBS.	900 SQ. FT.	1000 SQ. FT.
1/16"	.016	150'	125'	207 LBS.	230 LBS.	450 SQ. FT.	500 SQ. FT.
3/32"	.016	75'	65'	155 LBS.	179 LBS.	225 SQ. FT.	260 SQ. FT.
1/8"	.020	75'	65'	205 LBS.	237 LBS.	225 SQ. FT.	260 SQ. FT.
3/16"	.031	60'	45'	247 LBS.	247 LBS.	180 SQ. FT.	180 SQ. FT.
1/4"	.031	45'	35'	247 LBS.	256 LBS.	135 SQ. FT.	140 SQ. FT.
3/8"	.047	45'	35'	370 LBS.	384 LBS.	135 SQ. FT.	140 SQ. FT.
1/2"	.047	45'	35'	493 LBS.	511 LBS.	135 SQ. FT.	140 SQ. FT.
5/8"	.063	30'	30'	410 LBS.	547 LBS.	90 SQ. FT.	120 SQ. FT.
3/4"	.093	30'	30'	493 LBS.	658 LBS.	90 SQ. FT.	120 SQ. FT.
1"	.100	30'	25'	657 LBS.	730 LBS.	90 SQ. FT.	100 SQ. FT.

Maximum pieces per roll: 1/32"-3 pieces, 1/16" to 1/2"-2 pieces, 5/8" to 1" - 1 piece

Minimum piece length: 10'

Width tolerance: +1"/-1/2"

Length tolerance: 1/16" to 1/2" +/-10%, 5/8" to 1" +10%, Min. 10'

### Minimum Order:

Inventory Item: 1 Roll

Non-inventory Item: 2,000 lbs.

Custom Made Item: 3,000 lbs.

## AB-265 PHYSICAL PROPERTIES

DESCRIPTION	TYPICAL VALUE	UNITS
POLYMER	NBR/SBR/CR	
HARDNESS	60	SHORE "A" DUROMETER
TENSILE	1300	PSI
ELONGATION	500	%
OIL AGING # 1 OIL	70 HOURS	100 ° C
CHANGED-HARDNESS	-6	POINTS
CHANGED-TENSILE	-2	%
CHANGED-ELONGATION	-24	%
CHANGED-MASS	0	%
CHANGED-VOLUME	3	%

American Biltrite ISO 9001 manufactured product