



AMERICAN BILTRITE

AB-289

80 DURO NEOPRENE (55% CR BASE) / PREMIUM GRADE / SATIN FINISH /
VERY GOOD OIL RESISTANCE / UNTRIMMED / NO POWDER

GAUGE	ITEM NUMBER 36"	ITEM NUMBER 48"
SPECIFICATION: 2BC810B14C12A14EO34		
1/16"	283-04-362 (S)	283-04-482
3/32"	283-06-362 (S)	283-06-482
1/8"	283-08-362 (S)	283-08-482
3/16"	283-12-362 (S)	283-12-482
1/4"	283-16-362	283-16-482

(S) Normally available from inventory.

STANDARD DIMENSIONS

GAUGE	TOLERANCE (+/-)	ROLL LENGTH		APPROX. WEIGHT PER ROLL		APPROX. SQ. FT. PER ROLL	
		36"	48"	36"	48"	36"	48"
1/16"	.016	150'	150'	203 LBS.	270 LBS.	450 SQ. FT.	600 SQ. FT.
3/32"	.016	50'	65'	101 LBS.	174 LBS.	150 SQ. FT.	260 SQ. FT.
1/8"	.020	50'	50'	134 LBS.	178 LBS.	150 SQ. FT.	200 SQ. FT.
3/16"	.031	50'	50'	201 LBS.	268 LBS.	150 SQ. FT.	200 SQ. FT.
1/4"	.031	50'	50'	289 LBS.	358 LBS.	150 SQ. FT.	200 SQ. FT.

Maximum pices per roll: 2
Minimum piece length: 10'
Width tolerance: +1"/-1/2"
Length tolerance: +/-10%

Minimum Order:
Inventory Item: 1 Roll
Non-inventory Item: 2,000 lbs.
Custom Made Item: 3,000 lbs.

AB-289 PHYSICAL PROPERTIES

DESCRIPTION	TYPICAL VALUE	UNITS
POLYMER	CR/SBR	
HARDNESS	80	SHORE "A" DUROMETER
TENSILE	1000	PSI
ELONGATION	200	%
OIL AGING # 3 OIL	70 HOURS	100 ° C
CHANGED-HARDNESS	-37	POINTS
CHANGED-TENSILE	-43	%
CHANGED-ELONGATION	-37	%
CHANGED-MASS	28	%
CHANGED-VOLUME	45	%